

DuPont™ SentryGlas® INTERLAYER

Sealant Compatibility

Many different sealants are used in the glazing industry and it is important to understand the chemical and mechanical compatibility of these sealants with the interlayer fabricated in a glass laminate. Laminates prepared with SentryGlas® interlayer show excellent compatibility with different kinds of sealants used in various glazing applications.

DuPont Outdoor Testing of Sealant Compatibility

SentryGlas® laminates show no edge defect formation after 42-months of natural outdoor weathering in Florida when tested with different types of sealants:

DuPont™ SentryGlas® Sealant Test

C. R. Laurence 33SC	one component, acetic-cure, silicone
C. R. Laurence RTV408AL	one component, neutral-cure, RTV silicone
Dow Corning 995	one component, neutral-cure, silicone
Dow Corning 999-A	one component, acitoxo, silicone

SentryGlas® laminates show no degradation from interactions with any of the sealants tested. There has been no differentiation between the silicone/SentryGlas® interface and the SentryGlas®/air interface. DuPont continues to conduct extensive sealant compatibility studies, and further results can be obtained by contacting your local DuPont representative.



Independent Tests

An independent study done by GE Advanced Materials has been done with SentryGlas® laminates and various GE sealants. This has involved years of accelerated QUV weathering. The following sealants have been studied:

Independent Sealant Test—GE Advanced Materials

GE UltraGlaze® SSG4400	two component, neutral-cure, high modulus, silicone
GE UltraGlaze® SSG4000	one component, neutral-cure, high modulus, silicone
GE SilPruf NB SCS9000	one component, neutral-cure, medium modulus, silicone
GE IGS3729	one component, neutral-cure, high modulus, silicone

Laminates prepared with SentryGlas® show no visible defects.

An independent study by Dow Corning reviewed these sealants using a modified ASTM C1087 compatibility test method:

Independent Sealant Test—Dow Corning

Dow Corning® 756	one component, neutral-cure, medium modulus elastomeric silicone
Dow Corning® 790	one component, neutral-cure, ultra-low modulus silicone
Dow Corning® 791	one component, neutral-cure, architectural grade silicone
Dow Corning® 795	one component, neutral-cure, RTV silicone
Dow Corning® 983	two component, neutral-cure, RTV silicone
Dow Corning® 995	one component, neutral-cure, elastomeric silicone

The DuPont™ SentryGlas® structural interlayer was determined to be approved for full contact with each of the Dow Corning sealants studied. A Dow Corning laboratory report can be obtained upon request.

Worldwide DuPont Sales and Support

DuPont Glass Laminating Solutions supplies and supports customers from research, manufacturing and sales locations worldwide.

Americas

DuPont Company
BMP 26-2363
4417 Lancaster Pike
Wilmington, DE 19805 U.S.A.
Telephone +1 302 774 1161
Toll-free (USA) 800 438 7225
Fax +1 302 892 7390

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone +55 11 4166 8542
Fax +55 11 4166 8720

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86 21 3862 2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

sentryglas.com

The technical data contained herein are guides to the use of DuPont materials. The advice contained herein is based upon tests and information believed to be reliable, but users should not rely upon it absolutely for specific applications because performance properties will vary with processing conditions. It is given and accepted at user's risk and confirmation of its validity and suitability in particular cases should be obtained independently. The DuPont Company makes no guarantees of results and assumes no obligations or liability in connection with its advice. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see DuPont Medical Caution Statement, H-50102.

Copyright © 2008 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™ and SentryGlas® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

K-08776-3 (09/08) Printed in the U.S.A.



The miracles of science™